

PAINT INDUSTRIES PTY LTD

A.C.N. 008 753 839

TELEPHONE

(08) 9437 1488

FAX: (08) 9410 2395

61 Lionel Street
Naval Base 6165
WESTERN AUSTRALIA

P.O. BOX 83
North Fremantle 6159
WESTERN AUSTRALIA

MADE IN WA
GUARANTEED QUALITY
DATE: 31/01/2009

PRODUCT BULLETIN

P.S. 110

SUPA SEAL

0006

Description:

An oil based, pigmented sealer for use as a first coat on porous surfaces such as plaster, fibro cement, brick, cement render, masonry and hard board sheeting.

Properties:

Seals off the porosity of the substrate and provides an even surface for subsequent coatings. Provides some protection from action of mild alkali in substrate. Contains zinc oxide for mould resistance. Fills grain & sands easily where required e.g. hardboards which may "fur" on application.

Uses:

Formulated for first coating on porous surface such as plaster, fibro cement, brick, cement render, masonry & hard board sheeting, when being followed by a solvent based system. When thinned with 10% mineral turps, SUPA SEAL can be used as a sealer for plaster glass. Gyprock and other paper faced wall boards should not be sealed with SUPA SEAL. Use TOP DEK GYPSEAL.

Surface Preparation:

Allow new plaster to cure for 8 weeks and new cement render for 4 weeks. Ensure that all surfaces to be painted are free from all loose dirt, grime, mould, grease, loose plaster, or loose & flaking paint.

Moisture content of substrate should not exceed 15% when applying SUPA SEAL.

Efflorescence should be removed by washing down with a solution of 5% calcium chloride in water and allowed to dry thoroughly.

Mould should be treated with an appropriate bleach or sterilizing wash as directed.

Thinning:

Usually not necessary for general application. Thin 10% with mineral turps for application to plaster glass.

Application:

Preferably by brush but may be rolled or sprayed. Apply one full and even coat brushing well into the surface. On extremely porous surface applying a second coat will provide more even sealing..

Spread Rate:

Depending on the porosity of the surface, up to 10m² per litre may be achieved.

Drying Time:

At 25°C, touch dry in 1-2 hours. Recoat after 16 hours.

In cold & damp conditions allow longer times. Do not use when temperature is, or may fall below 10°C.

Clean-Up:

Clean all equipment immediately after use with mineral turps.

Standard Packaging:

10L 4L 2L 1L

Colour:

White. May be tinted with universal colourants.

This information is drawn from data which at the time of printing is believed by Paint Industries Pty Ltd to be accurate. Information is provided in good faith and as a general guide to users of the product. All persons using the product should enquire independently as to the suitability of the product for the end use and the application requirements for such use. Paint Industries Pty Ltd has no control over conditions under which products are stored handled or used and any recommendations cannot be regarded as a legal warranty or liability.