

PAINT INDUSTRIES PTY LTD

A.C.N. 008 753 839

TELEPHONE

(08) 9437 1488

FAX: (08) 9410 2395

61 Lionel Street
Naval Base 6165
WESTERN AUSTRALIA

P.O. BOX 83
North Fremantle 6159
WESTERN AUSTRALIA

MADE IN WA
GUARANTEED QUALITY
DATE: 31/01/2009

PRODUCT BULLETIN SC 610

TOPDEK GZP EPOXY 1026

Description: A two component, epoxy anti-corrosive primer pigmented with zinc phosphate.

Properties: For use on properly prepared surfaces in both new construction and as an industrial maintenance, primer for a range of anti-corrosive coating used in offshore, bridges & chemical & petro chemical industries.

Uses: GZP Epoxy is preferred for use with system for chemical environments, where zinc based materials can be subject to attack in both acidic & alkaline conditions.

Surface Preparation: Uncontaminated, rust free steel & irons.

Application: By brush, roller or spray.

Spread Rate: Approx 8m² / litre

Drying Time: At a surface temperature of 15°C, and 50% relative humidity.

Touch Dry: 1-2 hours
Recoat: Minimum 24 hours
Maximum 48 hours
Full Cure: 7 Days
Pot Life: 4-6 hours

(Application under 15°C, is not recommended. Protect against water contamination during initial stage – 72 hours. Times are reduced at increased temperatures or humidity).

Clean Up: Epoxy thinner.

Colour: Matt grey

Mixing Ratio: 3:1

This information is drawn from data which at the time of printing is believed by Paint Industries Pty Ltd to be accurate. Information is provided in good faith and as a general guide to users of the product. All persons using the product should enquire independently as to the suitability of the product for the end use and the application requirements for such use.

Paint Industries Pty Ltd has no control over conditions under which products are stored handled or used and any recommendations cannot be regarded as a legal warranty or liability.