

PAINT INDUSTRIES PTY LTD

A.C.N. 008 753 839

TELEPHONE
(08) 9437 1488
FAX: (08) 9410 2395

61 Lionel Street
Naval Base 6165
WESTERN AUSTRALIA

P.O. BOX 83
North Fremantle 6159
WESTERN AUSTRALIA

MADE IN WA
GUARANTEED QUALITY
DATE: 31/01/2009

PRODUCT BULLETIN

F.C. 302

ROLLTEX

0013

Description: Water based, high build acrylic flexible texture coating which has excellent waterproofing qualities. The texture profile can be varied greatly depending on application method and equipment used.

Properties: Interior or exterior application. Low sheen finish. Extremely flexible. Fills minor cracks & hides surface imperfections. High build application provides excellent waterproofing qualities.

Uses: As an exterior, textured finish on masonry, brick or rendered surfaces which requires covering & hiding of imperfections.

As a high build waterproofing coating on porous surfaces, walls & roofs.

Where an interior texture coating is required for aesthetic reasons or to hide imperfections.

Surface Preparation: All surfaces should be free from loose dirt, grime, mould, grease and loose or flaking paint.

Large holes or cracks should be filled with appropriate filler.

Gloss & semi gloss surfaces should be sand papered to provide a strong key.

Unpainted brick, plaster, fibro cement & masonry should be treated with one coat of TOP DEK ACRYLIC SEALER UNDERCOAT.

New or smooth trowelled concrete should be acid etched with a hydrochloric acid solution (1 part acid to 4 parts water) and rinsed clean before applying Acrylic Sealer Undercoat.

Thinning: For high profile texture application apply direct from the can. For airless spray application, Rolltex may be thinned with water up to 10%, keeping in mind that the film build will decrease accordingly.

Application: As a high profile texture coating apply one coat using a fine, medium or coarse texture roller, depending on the profile required. For a finer or low profile texture use a long nap Rolana type roller to apply one coat.

As a waterproof membrane application use a long nap roller or airless spray. Two coats should be used applying at the rate of 2m² per litre. Lower film builds will reduce the waterproofing capacity.

Spread Rate: Approx 2m² per litre when applied as a waterproofing membrane. Up to 6m² when used as a texture coating and dependant on method of application and type of roller used.

PAINT INDUSTRIES PTY LTD

2

PRODUCT BULLETIN

F.C. 302

Drying Time: At 25°C touch dry 2 – 4 hours. Recoat 6 – 8 hours.
Allow longer times in cold or damp conditions. Do not use if temperature is, or may fall below 10°C.

Clean-Up: Clean all equipment immediately with water.

Standard Packaging: 20L 10L 4L.

Colours: White – may be tinted. Special batch orders made to required colour.