

PAINT INDUSTRIES PTY LTD

A.C.N. 008 753 839

TELEPHONE
(08) 9437 1488

FAX: (08) 9410 2395

61 Lionel Street
Naval Base 6165
WESTERN AUSTRALIA

P.O. BOX 83
North Fremantle 6159
WESTERN AUSTRALIA

MADE IN WA
GUARANTEED QUALITY
DATE: 10/10/2016

PRODUCT BULLETIN

F.C. 338

FLUORESCENT FLOAT PAINT

LUNAR YELLOW 3025
BLAZE ORANGE 2026
AUSTRAL PINK 2017
LASER RED 3 1997

Description: A premium quality matt oil based, brilliant vibrant coloured fluorescent finish, for various properly prepared substrates. Suitable also for exterior application to brick, cement render, fibro cement and masonry.

Properties: An oil based, high opacity and durable finish with easy application. Has reasonable polish and wear resistance for a flat finish. Will fade in direct sunlight over time.

Uses: For use in interior and exterior applications, for the use in the sign writing industries, and excellent for fishing float identification. Has excellent fluorescent capabilities when applied two coats over white undercoat, and then used with a black light.

Surface Preparation: Allow new plaster to cure for 8 weeks and new cement render for 4 weeks. All surfaces must be thoroughly cleaned, dry and free of all loose dirt, dust, grease, mould, loose or flaking paint and loose surface plaster. Efflorescence or mould must be treated with the appropriate sterilising wash. Use solvent based pigmented sealer as first coat onto new unpainted plaster. To provide a key for better adhesion, lightly sandpaper gloss or semi gloss finishes and wipe clean.

Previously Painted Surfaces: Should be washed down with sugar soap as directed and where severe chalking is present apply a binding sealer. Fill all cracks, holes & surface damage with suitable filler and sandpaper smooth. Spot seal these areas with TOP DEK ACRYLIC SEALER UNDERCOAT.

Plaster Glass: **Must** be sealed with TOP DEK SUPASEAL. Gyprock or similar paper faced boards should be sealed with TOP DEK GYPSEAL.

For best results on, fibro, cement render, brick & masonry, polystyrene fishing floats, should be given one coat of TOP DEK ACRYLIC SEALER UNDERCOAT.

Thinning: For conventional or airless spray only, thin up to 10% with enamel thinners or mineral turpentine. Otherwise use directly from the can as supplied.

Application: Brush, roller or spray. Apply two full & even coats allowing a minimum of two hours between coats. When rolling use a medium nap (10mm) pure wool or synthetic roller. On rough surfaces use a longer nap roller. For best results use two coats over white undercoat

Spread Rate: Approximately 12 m² per litre, depending on porosity of surface.

Drying Time: At 25°C, touch dry 20-30 minutes. Recoat when dry after a minimum of 2 hours. In cold or damp conditions allow longer times. Do not use if temperature is, or may fall below 10°C.

Clean-Up: Clean all equipment immediately after use with mineral turpentine.

Standard Packaging: 4L & 1L only

Colours: Lunar Yellow, Blaze Orange, Austral Pink.

This information is drawn from data which at the time of printing is believed by Paint Industries Pty Ltd to be accurate. Information is provided in good faith and as a general guide to users of the product. All persons using the product should enquire independently as to the suitability of the product for the end use and the application requirements for such use. Paint Industries Pty Ltd has no control over conditions under which products are stored handled or used and any recommendations cannot be regarded as a legal warranty or liability.