

# PAINT INDUSTRIES PTY LTD

A.C.N. 008 753 839

TELEPHONE

(08) 9437 1488

FAX: (08) 9410 2395

61 Lionel Street  
Naval Base 6165  
WESTERN AUSTRALIA

P.O. BOX 83  
North Fremantle 6159  
WESTERN AUSTRALIA

MADE IN WA  
GUARANTEED QUALITY  
DATE; 31/01/2009

---

## PRODUCT BULLETIN

P.S. 111

---

### GREY ZINC PHOSPHATE PRIMER 2013

**Description:** A general purpose anti-corrosive primer for all iron, steel and all non-ferrous metals.

**Properties:** Solvent based and made on an alkyd resin formulation G.Z.P.P. has excellent rust inhibiting properties. Dries to a low sheen finish. Should be recoated with selected finish within 4-6 weeks of application for maximum performance, when used externally. Contains no chromate or lead pigments.

**Uses:** For protection of steelwork that is to be exposed externally prior to finishing coats being applied. Most conventional alkyd enamel finishes can be applied over G.Z.P.P.

**Surface Preparation:** Rust, mill scale and iron oxide deposits should be removed mechanically. All surfaces must be thoroughly degreased. The surfaces to be coated must be dry & primed within 2-4 hours of de-rusting and cleaning.

**Thinning:** Preferably apply direct from can but if thinning is required use a maximum of 5% mineral turpentine.

**Application:** Stir thoroughly with a broad flat paddle ensuring all pigment is incorporated. Apply by brush or spray one full coat direct from can.

**Spread Rate:** 10-12 square metres per litre @ 30-35 micron D.F.T.

**Drying Time:** Depending on atmospheric conditions G.Z.P.P. should be touch dry in 4 hours and may be recoated after 16 hours.

**Clean-Up:** Clean all equipment immediately after use with mineral turps.

**Standard Packaging:** 20L 4L 1L 500 ml & 250 ml

**Colour:** Grey.