

# PAINT INDUSTRIES PTY LTD

A.C.N. 008 753 839

TELEPHONE

(08) 9437 1488

FAX: (08) 9410 2395

61 Lionel Street  
Naval Base 6165  
WESTERN AUSTRALIA

P.O. BOX 83  
North Fremantle 6159  
WESTERN AUSTRALIA

MADE IN WA  
GUARANTEED QUALITY  
DATE: 31/01/2009

---

## PRODUCT BULLETIN

U.C. 202

---

### ALL PURPOSE UNDERCOAT

0001

**Description:** A long oil alkyd based undercoat for interior & exterior use on a wide range of substrates.

**Properties:** Has excellent opacity & filling capacities. Provides superb hold-out & gloss development when overcoated with enamels. Outstanding sand papering qualities.

**Uses:** As an all purpose undercoat on suitably prepared interior & exterior timber and metal surfaces. Over correctly primed or sealed wall board, brick, masonry & fibro cement.  
Particularly suitable as an undercoat for oil based interior or exterior enamels.

**Surface Preparation:** Ensure that all surfaces to be painted are free from all loose dirt, grime, mould, grease & loose or flaking paint.

**Previously Painted Surfaces:** Sand paper gloss or semi gloss surfaces, removing loose or flaking paint and any chalkiness of the surface. Wash down with Sugar Soap.

Fill imperfections with appropriate filler and sand paper smooth.

Spot prime exterior base timber areas with TOP DEK PINK PRIMER.

**New Timber:** For interior application, first fill any imperfections with appropriate filler and sand paper the whole area to be coated assuming that the filled areas are smooth.

Exterior timber should be filled, sand papered and one coat of TOP DEK PINK PRIMER applied.

**Iron & Steel:** Remove all rust and mill scale and apply one coat of TOP DEK RED OXIDE ZINC PHOSPHATE PRIMER to bare metal.

Seal plaster, concrete, brick, cement render, fibro cement and masonry with TOP DEK SUPA SEAL as directed.

Gyprock & paper faced boards should be sealed with TOP DEK GYPSEAL.

Plaster Glass must be sealed with TOP DEK SUPA SEAL.

# PAINT INDUSTRIES PTY LTD

- 2 -

---

## PRODUCT BULLETIN

---

U.C. 202

**Thinning:** Not generally required. Apply direct from the can. If thinning is required for spraying add up to 5% mineral turps or Spraying Enamel Thinners.

**Application:** Brush, roller or spray. Apply one or two coats to the prepared area allowing 16 hours to dry and lightly sanding between coats.

**Spread Rate:** Approx. 16m<sup>2</sup> per litre per litre depending on porosity of surface.

**Drying Time:** At 25°C touch dry in 2-4 hours; recoat after 16 hours. In cold or damp conditions allow longer times. Do not use if temperature is, or may fall below 10°C.

**Clean-Up:** Clean all equipment immediately after use with mineral turps.

**Standard Packaging:** 10L 4L 2L 1L 500 ml 250 ml

**Colours:** White. May be tinted with universal colourants if necessary.

This information is drawn from data which at the time of printing is believed by Paint Industries Pty Ltd to be accurate. Information is provided in good faith and as a general guide to users of the product. All persons using the product should enquire independently as to the suitability of the product for the end use and the application requirements for such use. Paint Industries Pty Ltd has no control over conditions under which products are stored handled or used and any recommendations cannot be regarded as a legal warranty or liability.